



## PHIẾU BÁO KẾT QUẢ THỬ NGHIỆM

Số TN: 22-03-04-20-2/TNV-2

Ngày phát hành: 06-04-2020

Tên khách hàng: CÔNG TY CỔ PHẦN DỆT HÒA KHÁNH ĐÀ NẴNG

Địa chỉ: Lô B, Đường số 9, Khu công nghiệp Hòa Khánh, P. Hòa Khánh Bắc, Q. Liên Chiểu, TP. Đà Nẵng

Ngày nhận mẫu: 03-04-2020

Ngày thực hiện: Từ 03-04-2020 đến 06-04-2020

Mẫu được cung cấp và nhận dạng bởi khách hàng

Tên mẫu: Mẫu 4A < Màu Xanh >

Mẫu kiểm tra:



Kết quả thử nghiệm:

TT	Chỉ tiêu	Phương pháp thử	Kết quả
1	Tính kháng thấm nước bề mặt- Phép thử phun tia (Spray test)	AATCC 22-2017	90

- Ghi chú:
- + 0: Ngấm ướt hoàn toàn trên toàn bộ bề mặt mẫu.
  - + 50: Ngấm ướt hoàn toàn trên bề mặt mẫu vượt ra ngoài điểm phun tia.
  - + 70: Ngấm ướt một phần trên bề mặt mẫu vượt ra ngoài điểm phun tia.
  - + 80: Có vết ướt trên bề mặt mẫu tại thời điểm phun tia.
  - + 90: Có vết ướt nhẹ ngẫu nhiên trên bề mặt mẫu.
  - + 100: Bề mặt mẫu không bị ngấm ướt.

THỦA ỦY QUYỀN CHỦ TỊCH H.Đ.Q.T



GIAM ĐỐC TRUNG TÂM THÍ NGHIỆM

Kết quả thử nghiệm chỉ đại diện cho mẫu do khách hàng cung cấp: 1,0m x khổ

Không được sao chép một phần bản kết quả này nếu không được sự đồng ý bằng văn bản của Viện Nghiên cứu Dệt may

Tên mẫu, tên khách hàng được ghi theo yêu cầu của khách hàng.



**TEST REPORT**

Test No: 22-03-04-20-2/TNV-2  
 Date of issue: April 6<sup>th</sup>, 2020

Client: DANATEX

Address: No. 5 Lot B, No. 9 road, Hoa Khanh Industrial Park, Hoa Khanh Bac Ward, Lien Chieu, Da Nang


Date of receipt: April 3<sup>rd</sup>, 2020

Date of performance: From April 3<sup>rd</sup>, 2020 to April 6<sup>th</sup>, 2020

Sample provided and identified by client:

Sample Identification: Fabric 4A <Blue>

Test Sample:



Test result:

No	Item	Test method	Result
1	Water repellency: Spray test	AATCC 22-2017	90

Note: Assesment following to the rating chart:

- + 0: complete wetting of the entire face of the specimen.
- + 50: complete wetting of the entire specimen face beyond the spray points.
- + 70: partial wetting of the specimen face beyond the spray points.
- + 80: wetting of specimen face at spray points.
- + 90: slight random sticking or wetting of the specimen face.
- + 100: no sticking or wetting of the specimen face.

SIGNED FOR AND ON BEHALF OF VTRI



GIÁM ĐỐC TRUNG TÂM THÍ NGHIỆM

*Đỗ Chí Hải Nam*

The above results are valid for tested samples provided by applicant only: 10cm full width.  
 Reproduction apart of this Test Report is not allowed without permission written of Textile Testing Centre  
 Client, Sample identification and Manufacturer are introduced at client's requests.